



PRODUCT TESTING SERVICE

100 Clemson Research Blvd. □ Anderson, SC 29625 □ Tel (864) 646-TILE □ Fax (864) 646-2821

October 29, 2013

MS International, Inc.
Attn: Morgan Huang
2095 N. Batavia St.
Orange, CA 92865

Dear Morgan Huang,

Tile Council of North America has tested the samples you submitted. Test report TCNA-677-13 is enclosed. If you have any questions or concerns, please contact us.

Best Regards,

TILE COUNCIL OF NORTH AMERICA, INC.

Dr. Jyothi Rangineni
Research Scientist
Enclosures



PRODUCT TESTING SERVICE

100 Clemson Research Blvd. □ Anderson, SC 29625 □ Tel (864) 646-TILE □ Fax (864) 646-2821

TCNA TEST REPORT NUMBER:

TCNA-677-13

PAGE: 1 OF 1

TEST REQUESTED BY:

MS International, Inc.
Attn: Morgan Huang
2095 N. Batavia St.
Orange, CA 92865

TEST SUBJECT MATERIAL:

Identified by client as: “Sophie Line”

TEST DATE:

10/24/2013

TEST PROCEDURE:

ASTM C1028: “Standard Test Method for Determining the Static Coefficient of Friction of Ceramic Tile and Other Like Surfaces by the Horizontal Dynamometer Pull-Meter Method”

-A Chatillon DFIS 100 digital force gauge was used to measure each pull in pounds-force.

-A 3 x 3 x 1/8-inch piece of Neolite was used as the sensor.

TEST RESULTS:

The average static coefficient of friction of four (4) pulls on each tile was as follows:

	<u>As Received</u>	<u>After Cleaning</u>
<u>Tile 1</u>		
Dry	0.76	0.76
Wet	0.57	0.56
<u>Tile 2</u>		
Dry	0.76	0.77
Wet	0.56	0.57
<u>Tile 3</u>		
Dry	0.76	0.77
Wet	0.56	0.56

The average static coefficient of friction of twelve (12) pulls was as follows:

	<u>As Received</u>	<u>After Cleaning</u>
Dry	0.76	0.76
Wet	0.56	0.56

10/29/2013

Dr. Jyothi Rangineni
Research Scientist

Testing Services: testing@tileusa.com □ Literature Orders: literature@tileusa.com □ Web Site: www.tileusa.com

This report is confidential and has been prepared for the exclusive use of the client. It is not an endorsement, approval, certification, or criticism of any product by TCNA. This report shall not be published in any form without prior written consent from TCNA