

TEST REPORT

DATE: 09-25-2025

Page 1 of 1

TEST NUMBER: 0322488

CLIENT	MS International, Inc. - CA
--------	-----------------------------

TEST METHOD CONDUCTED	ASTM C1243 Standard Test Method for Relative Resistance to Deep Abrasive Wear of Unglazed Ceramic Tile by Rotating Disc
-----------------------	---

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Regallo Collection
COLOR	Calacatta Isla
CONSTRUCTION	Porcelain Tile

PURPOSE

This test method measures the deep abrasive wear of unglazed ceramic tile by quantifying loss of volume under controlled abrasion. It's intended to assess durability (resistance to wear), rather than surface appearance.

TEST SPECIMENS & SAMPLING

Use whole tiles or suitably sized specimens fixed (e.g. with adhesive) to a backing or larger substrate, avoiding joints when possible.

A minimum of five tiles (or test specimens) should be tested to obtain representative data. Tiles must show no visible warpage, verified (for example with a straightedge), before testing.

PROCEDURE

1. Mount specimen so its face is tangentially in contact with the rotating disc.
2. Feed abrasive uniformly with the specified rate (100 g \pm 10 g per 100 revolutions) into the grinding zone.
3. Rotate disc for 150 revolutions under calibrated pressure.
4. After test, measure the chord length (wear scar) produced on the specimen. The chord is the linear distance across the worn region.
5. From chord(s) and specimen geometry, calculate the volume loss. The test yields relative resistance values (i.e. how much volume was worn away).
6. Compare results across specimens or against reference materials.

	CHORD LENGTH	VOLUME LOSS
SPECIMEN 1	20.0 mm	67 mm ³
SPECIMEN 2	20.5 mm	72 mm ³
SPECIMEN 3	20.0 mm	67 mm ³
SPECIMEN 4	20.5 mm	72 mm ³
SPECIMEN 5	21.0 mm	77 mm ³
AVERAGE VOLUME (mm³)		71 mm ³

COMMENTS:

Volume values are from Table 1 of the test method.

APPROVED BY: Brandon Stokes

Lab Director -

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products.

This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.